

## Multi-Cure® 984-LVF Conformal Coating

Multi-Cure 984-LVF is a single-component, 100% solids, conformal coating specifically formulated for rapid room temperature cure when exposed to longwave (320-380 nanometer) UV light. Thin layer coatings cure almost instantly to a depth of 7 mils and fluoresce upon exposure to black light. Multi-Cure 984-LVF also exhibits excellent adhesion to a variety of metal, ceramic, and glass-filled epoxy surfaces. 984-LVF is a moderately low viscosity coating which can be cured by exposure to UV light and secondarily with heat for shadowed areas on densely populated circuit boards. This product is in full compliance with RoHS directives 2015/863/EU. 984-LVF is UL recognized (UL 746C/94), rated indoor/outdoor at 120°C.

Multi-Cure 984-LVF is approved to Military Specification MIL-I-46058-C, Type AR, ER, and UR (QPL#576-90). 984-LVF meets "NSA" hydrolytic stability (reversion) requirements.

### TYPICAL UNCURED PROPERTIES

Solvent Content	None	
Appearance	Single Component/Colorless Fluorescing Liquid	
Specific Gravity	1.05	
Viscosity	150 cP (nominal)	ASTM D-1384

### TYPICAL CURED PROPERTIES

#### PHYSICAL

Durometer Hardness	D80	ASTM D-224
Tensile at Break	6,000 psi	ASTM D-638
Elongation at Break	5%	ASTM D-638
Modulus of Elasticity	60,000 psi	ASTM D-638
Water Absorption	0.4%	ASTM D-570
Cross Hatch Adhesion Test:	Copper 100%	ASTM D-3359
	G-10 100%	ASTM D-3359

#### THERMAL

Thermal Limit (brittle/degrades)	-55° to 175°C (-65° to 350°F)	DSTM* D-200
Coefficient of Linear Thermal Expansion	69 x 10 <sup>-6</sup> in/in/°C	ASTM E-831

#### ELECTRICAL

Dielectric Strength	1,800 V/mil	ASTM D-1304
Volume Resistivity	35.8 x 10 <sup>12</sup> ohm-cm	ASTM D-1304
Surface Resistivity	384 x 10 <sup>12</sup> ohm	ASTM D-1304
Dissipation Factor, 1 MHz	0.03	ASTM D-1304
Dielectric Constant, 1 MHz	3.4	ASTM D-1304

\*DSTM refers to Dymax Standard Test Method



© 2000-2015 Dymax Corporation. All rights reserved. All trademarks in this guide, except where noted, are the property of, or used under license by Dymax Corporation, U.S.A.

Technical data provided is of a general nature and is based on laboratory test conditions. Dymax does not warrant the data contained in this bulletin. Any warranty applicable to the product, its application and use is strictly limited to that contained in Dymax standard Conditions of Sale published on our website. Dymax does not assume responsibility for test or performance results obtained by users. It is the user's responsibility to determine the suitability for the product application and purposes and the suitability for use in the user's intended manufacturing apparatus and methods. The user should adopt such precautions and use guidelines as may be reasonably advisable or necessary for the protection of property and persons. Nothing in this communication shall act as a representation that the product use or application will not infringe on a patent owned by someone other than Dymax or act as a grant of license under any Dymax Corporation Patent. Dymax recommends that each user adequately test its proposed use and application before actual repetitive use, using the data in this communication as a general guideline. Technical Data Collection Prior to 2000 REV. 12/20/2018

Dymax Corporation  
+1.860.482.1010 | info@dymax.com | [www.dymax.com](http://www.dymax.com)

Dymax Europe GmbH  
+49 611.962.7900 | info\_de@dymax.com | [www.dymax.de](http://www.dymax.de)

Dymax Engineering Adhesives Ireland Ltd.  
+353 21.237.3016 | info\_ie@dymax.com | [www.dymax.ie](http://www.dymax.ie)

Dymax Oligomers & Coatings  
+1.860.626.7006 | info\_oc@dymax.com | [www.dymax-oc.com](http://www.dymax-oc.com)

Dymax UV Adhesives & Equipment (Shanghai) Co. Ltd.  
+86.21.37285759 | dymaxasia@dymax.com | [www.dymax.com.cn](http://www.dymax.com.cn)

Dymax UV Adhesives & Equipment (Shenzhen) Co. Ltd.  
+86.755.83485759 | dymaxasia@dymax.com | [www.dymax.com.cn](http://www.dymax.com.cn)

Dymax Asia (H.K.) Limited  
+852.2460.7038 | dymaxasia@dymax.com | [www.dymax.com.cn](http://www.dymax.com.cn)

Dymax Asia Pacific Pte. Ltd.  
+65.6752.2887 | info\_ap@dymax.com | [www.dymax-ap.com](http://www.dymax-ap.com)

Dymax Korea LLC  
+82.2.784.3434 | info\_kr@dymax.com | [www.dymax.com/kr](http://www.dymax.com/kr)

**CURE SCHEDULE** - UV Cure with 365 nm UV light <sup>[1]</sup>:

Cure Time (seconds)	Intensity mW/cm <sup>2</sup>	Dymax Light-Welder <sup>®</sup> Lamp
30	250	5000-EC
1	2,500	UVC-6 with F-450

Multi-Cure 984-LVF is designed with optimum level of fluorescent indicator to allow cure and to fluoresce under a black light. Though UV conformal coatings do not fluoresce as brightly as traditional solvent based coatings, the following steps should permit adequate brightness for easy inspection:

1. Avoid overcuring the conformal coating. The UV cure schedule listed above is adequate. Lengthening exposure to UV light lowers fluorescence.
2. Inspect coated boards under black light in a shrouded area. Indirect indoor lighting decreases the effect of the black light in revealing the fluorescence.

**Heat Cure Following UV Exposure**

Heat can be used as a secondary cure mechanism where all adhesive cannot be cured with UV light. UV cure must be done prior to heat cure. Application may involve dip, spray, or curtain coat. The following cure schedule may be used:

110°C	225°F	1 hour
120°C	250°F	30 minutes
150°C	300°F	15 minutes

**FACTORS AFFECTING CURING**

- ◆ Dark surfaces lengthen cure time. Thicker films require longer cure times.
- ◆ Full range (UV-A, B & C) lamps provide faster cures than filtered sources.
- ◆ All UV sources degrade with use. Check output periodically with a radiometer.
- ◆ Light intensity decreases as distance from UV source increases.

**HANDLING AND DISPENSING ADHESIVE**

Typically, Dymax 984-LVF is sprayed. For questions relating to dispensing, curing systems, or the use of Dymax products, contact Dymax Application Engineering.

Repeated or continuous skin contact may cause sensitization and should be avoided. Do not wear jewelry. The use of barrier hand cream is recommended. Do not wear absorbent gloves. Adhesive may be removed with hand soap and water. Avoid eye contact. See CAUTION below. Wipe excess adhesive with paper towels; remove residue with chlorinated solvents, freon, methanol, ethanol, or isopropanol.

**STORAGE AND SHELF LIFE**

Store the material in a cool, dark place when not in use. Do not expose to light. This product may polymerize upon prolonged exposure to ambient and artificial light. Keep covered when not in use. This material has an 18-month shelf life from date of manufacture, unless otherwise specified, when stored between 10°C (50°F) and 35°C (90°F) in the original, unopened container. Dymax product 984-LVF does not support fungal or bacterial growth.

**CAUTION**

For industrial use only. Avoid breathing vapors. Avoid contact with eyes and clothing. In case of contact, immediately flush with water for at least 15 minutes; for eyes, get medical attention. Wash clothing before reuse. Keep out of reach of children. Do not take internally. If swallowed, vomiting should be induced at once and a physician called. For specific information, refer to the product's Material Safety Data Sheet before use.

**GENERAL INFORMATION**

This product is intended for industrial use only. Keep out of the reach of children. Avoid breathing vapors. Avoid contact with skin, eyes, and clothing. Wear impervious gloves. Repeated or continuous skin contact with uncured material may cause irritation. Remove material from skin with soap and water. Never use organic solvents to remove material from skin and eyes. For more information on the safe handling of this material, please refer to the Safety Data Sheet before use.

The data provided in this document are based on historical testing that Dymax performed under laboratory conditions as they existed at that time, and are for informational purposes only. The data are neither specifications nor guarantees of future performance in a particular application. Dymax does not guarantee that this product's properties are suitable for the user's intended purpose.

Numerous factors—including, without limitation, transport, storage, processing, the material with which the product is used, and the ultimate function or purpose for which the product was obtained—may affect the product's performance and/or may cause the product's actual behavior to deviate from its behavior in the laboratory. None of these factors are within Dymax's control. Conclusions about the behavior of the product under the user's particular conditions, and the product's suitability for a specific purpose, cannot be drawn from the information contained in this document.

It is the user's responsibility to determine (i) whether a product is suitable for the user's particular purpose or application and (ii) whether it is compatible with the user's intended manufacturing process, equipment, and methods. Under no circumstances will Dymax be liable for determining such suitability or compatibility. Before the user sells any item that incorporates Dymax's product, the user shall adequately and repetitively test the item in accordance with the user's procedures and protocols. Unless specifically agreed to in writing, Dymax will have no involvement in, and shall under no circumstances be liable for, such testing.

Dymax makes no warranties, whether express or implied, concerning the merchantability of this product or its fitness for a particular purpose. Nothing in this document should be interpreted as a warranty of any kind. Under no circumstances will Dymax be liable for any injury, loss, expense or incidental or consequential damage of any kind allegedly arising in connection with the user's handling, processing, or use of the product. It is the user's responsibility to adopt appropriate precautions and safeguards to protect persons and property from any risk arising from such handling, processing, or use.

The specific conditions of sale for this product are set forth in Dymax's Conditions of Sale which are available at <https://www.dymax.com/index.php/en/resources/sales-terms-conditions>. Nothing contained herein shall act as a representation that the product use or application is free from patents owned by Dymax or any others. Nothing contained herein shall act as a grant of license under any Dymax Corporation Patent.

Except as otherwise noted, all trademarks used herein are trademarks of Dymax. The "®" symbol denotes a trademark that is registered in the U.S. Patent and Trademark Office.

The contents of this document are subject to change. Unless specifically agreed to in writing, Dymax shall have no obligation to notify the user about any change to its content.